

## Immunization Grade Mouse Type II Collagen, Lyophilized

Catalog # 20061

*For Research Use Only - Not Human or Therapeutic Use*

DESCRIPTION:	Highly purified type II collagen (treated with 3M guanidine, DEAE-cellulose, and Na <sub>2</sub> HPO <sub>4</sub> )
APPLICATION:	Can be used for various purposes, such as a standard for collagen analysis by SDS-gel, substrate for MMP-1, MMP-8, and MMP-13, and as an antigen for immunizing animals for the induction of collagen-induced arthritis ( <a href="#">CIA</a> ) in certain species and strains of experimental animals.
QUANTITY:	1 mg
FORM:	Lyophilized powder
SOURCE:	Mouse sternal cartilage
MOLECULAR WEIGHT:	300 kDa
PURITY:	>99% by SDS-PAGE, free of pepsin and proteoglycans
STORAGE:	4°C in the dark
STABILITY:	2 years
NOTES:	<p>Soluble in acidic buffer (maximum 4 mg/ml), but difficult to dissolve in neutral buffer. In order to dissolve this product in a neutral buffer, first dissolve collagen in 0.01M or 0.05M acetic acid at 1-4 mg/ml and then add this collagen solution to the desired neutral buffer such as 2-10X Tris-NaCl (NaCl final concentration: 0.15-0.2M) or dialyze against 1X neutral buffer at 4°C.</p> <p>NOTE 1: To avoid fibril formation under neutral conditions, keep solution on ice.</p> <p>NOTE 2: The physicochemical property of type II collagen differs from type I collagen and type II collagen dissolved in a neutral buffer does not form a stable gel incubating at 37°C. In order to prepare a type II collagen gel, additional components such as type I collagen or other substances may be required.</p>
REFERENCES:	<p>R. Trelstad, <i>et al. Biochemistry</i> <b>9</b>: 4993-4998 (1970)</p> <p>E. Miller, <i>Biochemistry</i> <b>10</b>: 1652-1659 (1971)</p> <p>D. Trentham, <i>et al. J. Exp. Med.</i> <b>146</b>: 857-868 (1977)</p> <p>P. Wooley, <i>et al. J. Immunology</i> <b>135</b>: 2443-2451 (1985)</p>