Immunization Grade Chick Type II Collagen, Lyophilized

Catalog # 20011

For Research Use Only - Not Human or Therapeutic Use

DESCRIPTION:	Highly purified type II collagen (treated with 3M guanidine, DEAE-cellulose, and Na2HPO4)
APPLICATION:	Can be used for various purposes, such as a standard for collagen analysis by SDS-gel, substrate for MMP-1, MMP-8, and MMP-13, and as an antigen for immunizing animals for the induction of collagen-induced arthritis (CIA) in certain species and strains of experimental animals.
QUANTITY:	10 mg
FORM:	Lyophilized powder
SOURCE:	Chicken sternal cartilage
MOLECULAR WEIGHT:	300 kDa
PURITY:	>99% by SDS-PAGE, free of pepsin and proteoglycans
STORAGE:	4°C in the dark
STABILITY:	2 years
NOTES:	Soluble in acidic buffer (maximum 4 mg/ml), but difficult to dissolve in neutral buffer. In order to dissolve this product in a neutral buffer, first dissolve collagen in 0.01M or 0.05M acetic acid at 1-4 mg/ml and then add this collagen solution to the desired neutral buffer such as 2-10X Tris-NaCl (NaCl final concentration: 0.15-0.2M) or dialyze against 1X neutral buffer at 4°C. Chondrex, Inc. offers Cat # 9075, Collagen Solubilizing Buffer (0.05M acetic acid), as a companion product for dissolving or diluting collagen. NOTE 1: To avoid fibril formation under neutral conditions, keep solution on ice. NOTE 2: The physicochemical property of type II collagen differs from type I collagen and type II collagen dissolved in a neutral buffer does not form a stable gel incubating at 37°C. In order to prepare a type II collagen gel, additional components such as type I collagen or other substances may be required.
REFERENCES:	R. Trelstad, *et al. Biochemistry* **9**: 4993-4998 (1970) E. Miller, *Biochemistry* **10**: 1652-1659 (1971) D. Trentham, *et al. J. Exp. Med*. **146**: 857-868 (1977) P. Wooley, *et al. J. Immunology* **135**: 2443-2451 (1985)

© 2024 Chondrex, Inc. All Rights Reserved, 20011 2.1

16928 Woodinville-Redmond Rd NE Suite B-101
Woodinville, WA 98072

Phone: 425.702.6365 or 888.246.6373
Fax: 425.882.3094

www.chondrex.com
support@chondrex.com